



PRODUCT DATA SHEET

Sikalastic® Rapid Thixo

Viscosity-Increasing additive

PRODUCT DESCRIPTION

Sikalastic® Rapid Thixo is an additive used with Sikalatic Rapid resins to increase resin viscosity when applied on steep slopes or vertical substrates.

USES

Used to increase Sikalastic Rapid resin viscosity when applied on steep slopes or vertical substrates.

CHARACTERISTICS / ADVANTAGES

- Easy to mix

PRODUCT INFORMATION

Chemical Base	Liquid
Packaging	0.26 gal (1.0 L) pails, 2.6 lb (1.18 kg) per pail
Shelf Life	Up to 12 months in the original unopened pail when properly stored, sealed and unmixed.
Storage Conditions	Store in a tightly closed container in a cool, dry, ventilated area away from heat and oxidizing agent. Do not store in direct sunlight or in temperatures below 55°F (13°C) or above 80°F (27°C).
Volatile organic compound (VOC) content	See Product Safety Data Sheet
Waiting Time	20 to 30 minutes before use.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

AVAILABILITY/WARRANTY

AVAILABILITY

From Sika Corporation – Sika Authorized Applicators for use within Sika membrane systems.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

MIXING

For vertical substrates or slopes exceeding 1-1/2 : 12, pre-mix the required Sikalastic Rapid resin with Sikalastic® Rapid Thixo at up to 2% addition by weight. The amount of Sikalastic® Rapid Thixo needed will vary by slope and temperature. Test the amount of Sikalastic® Rapid Thixo required by mixing small batches before mixing entire units of product. Resin mixed with Sikalastic® Rapid Thixo must be allowed to stand 20 to 30 minutes before use.

NOTE:

Storage and working times of Sikalastic Rapid resins are not affected by the addition of Sikalastic® Rapid Thixo.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD**

BY OTHERS.

Sale of Sika products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/about-us/terms-conditions-of-sale.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet
Sikalastic® Rapid Thixo
May 2026, Version 02.01
020915402000246375

SikalasticRapidThixo-en-US-(05-2026)-2-1.pdf

